

Doctor Iron Metal Finish

Pat Macarty gave the following at LAMA conference in March 2015. The metal coating is to protect metal for about 1 year before recoat is required. The finish is less tacky and attracts less dust.

Ingredients

1 Quart Boiled Linseed Oil

1 Pint Spar Varnish(used for boat wood-has UV Protection)

Golf Ball Size Beeswax

1 Quart Turpentine

Directions

Melt Beeswax, Boiled Linseed Oil, and Spar Varnish in Double Boiler in can.

First, the double boiler should have water in it.

Second, place the metal can with the 3 ingredients. In water until all melted.

Third, once all melted remove from boiler and add turpentine and stir till all mixed.

Note – makes a little over 2 quarts of metal finish